Amendments to the Claims:

This listing of claims will replace all prior versions and listings of claims in the application:

Listing of Claims:

1. (Currently Amended) A panel comprising:

fibers;

starch; and

a latex, wherein the latex comprises is incorporated within the panel in an amount from about 0.01% to 0.97% of the panel by weight on a dry weight percent basis and forms an ultra thin, water-impermeable coating on the fibers within the panel such that water may flow through a cross section of the panel.

- 2. (Original) The panel of claim 1, wherein the latex further comprises a functional group selected from the group consisting of carboxylic acid, methylol, hydroxyl, urethane, amide, urea and combinations thereof.
- 3. (Original) The panel of claim 2, wherein carboxylic acid comprises from about 0.02% to about 7% by weight of the latex.
- 4. (Currently Amended) The panel of claim 1, wherein the latex comprises from about 0.01% to about 0.5% of the panel by weight on a dry weight percent basis.

Appl. No. 10/698,123 Response Dated October 7, 2004 Response to Official Action of June 7, 2004

5. (Currently Amended) A coated panel comprising:

fibers;

starch;

a latex, wherein the latex eomprises is incorporated within the panel in an amount from about 0.01% to 0.97% of the panel by weight on a dry weight percent basis and forms an ultra thin, water-impermeable coating on the fibers within the panel such that water may flow through a cross section of the panel; and

a coating including a chelating agent applied to a facing side of the panel.

- 6. (Original) The panel of claim 5, wherein the coating further comprises a binder and a filler.
- 7. (Original) The panel of claim 5, wherein the latex further comprises a functional group selected from the group consisting of carboxylic acid, methylol, hydroxyl, urethane, amide, urea and combinations thereof.
- 8. (Original) The panel of claim 7, wherein carboxylic acid comprises from about 0.02% to about 7% by weight of the latex.
- 9. (Currently Amended) The panel of claim 5, wherein the latex comprises from about 0.01% to about 0.5% of the panel by weight on a dry weight percent basis.